

Product Data for Style 1600

Construction: Plaited from premium grade, long-line, high tensile strength ramie/flax yarn and sealed with a superior waterproof, tallow base lubricant.

pH Range: 6 – 9 (Brines, cold water and oils)

Temperature Limit: -10°F to 200°F (-23°C to 93°C)

Pressure Limit: 150 psi (10 bar)

Shaft Speed: 1000 fpm

Service: Designed particularly for marine stern tubes, bilge pumps and rudder posts.



Product Data for Style 1613

Construction: Plaited from long-fiber flax impregnated with TFE and lubricated to provide a flexible, formable and long-service packing.

pH Range: 6 – 9 (Brines, cold water and oils)

Temperature Limit: -10°F to 220°F (-23°C to 104°C)

Pressure Limit: 300 psi (21 bar)

Shaft Speed: 1200 fpm

Service: Designed particularly for marine stern tubes, bilge pumps and rudder posts.



How to Order

Specify: style number, size, quantity and packaging desired

Size	in	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	11/16"	3/4"	13/16"	7/8"	15/16"	1"
	mm	3,20	4,80	6,40	7,90	9,50	11,10	12,70	14,30	15,90	17,50	19,10	20,60	22,20	23,80	25,40
1600	ft/lb	101,00	40,37	36,96	20,00	13,30	10,00	8,00	6,40	5,10	4,30	3,80	3,20	2,70	2,40	2,15
	M/kg	67,67	27,05	24,76	13,40	8,90	6,77	5,36	4,29	3,42	2,88	2,50	2,14	1,81	1,61	1,44
1613 Length (±10%)	ft/lb	90,48	48,00	28,00	19,00	13,00	10,00	8,00	6,10	5,40	4,50	3,70	3,20	2,90	1,25	1,20
	M/kg	68,30	32,16	18,76	12,73	8,71	6,69	5,36	4,09	3,62	3,02	2,48	2,14	1,94	0,84	0,80
Packaging	*Sizes 1/8" through 1/2" available in 1 lb. spools. All sizes available in 5 and 10 lb. boxes; 25 and 50 lb. reels.															

Distributed by

A Greene, Tweed Company
Denton Industrial Park
25 Engerman Ave., Denton, MD 21629
Phone: +1.410.479.2244, Fax: +1.410.479.0836
E-mail: info@palmettopackings.com
Website: www.palmettopackings.com

Product data is based upon our experience and knowledge of typical applications and should be used to determine approximate service compatibility.

All trademarks are property of their respective owners.
Printed in USA ©2014 Palmetto®
08/14-GT DS-US-PI-195